

ARCICAST 47

CHEMICAL ANALYSIS (Standard)		
%	typical	Guaranteed
Al ₂ O ₃	47.07	Min 46,0
SiO ₂	48.46	
Fe ₂ O ₃	1,16	Max 1,5
TiO ₂	2.97	—
CaO	0.19	—
MgO	0.08	—
Na ₂ O	0,01	Max 0,3
K ₂ O	0.08	

PHYSICAL PROPERTIES			
	typical	Guaranteed	
Bulk Density	2,59	2,50	g/cm ³
Water absorption	1.70	—	%
Apparent porosity	4	—	%