

AUSTRALIAN MAGNESITE

Chemical Analysis		
%	Typical	Guaranteed
Al ₂ O ₃	0,11	Max 0.2
SiO ₂	0,65	Max 0.8
Fe ₂ O ₃	0,20	Max 0.3
CaO	2,20	Max 2.70
MgO	96,60	

Physical Properties			
	Typical	Guaranteed	
Bulk density	3.41	3.40	g/cm ³
Tamaño de cristal de periclasa	130	105	µm

Mineralogical Composition	
Main Phase	Magnesia
Secondary Phase	

Other Information