

BENTHUL 70

Technical Specifications

	Typical	Guaranteed
Moisture	7-8 %	11 % max
Ash Content	59-69 %	49-71 %
Volatile matter	6-14 %	4-20 %
Sulphur	0.2 %	0,8 % max
% Passing through sieve 63 μ	70 %	50 % min

Other Information

Benthul 70 is a mixture of bentonite and coal in a 30:70 ratio, with a sulphur content, volatile matter, ash content and swelling index suitable for its application. Benthul 70 has many advantages. On the first hand, the amount of bentonite present in the product improves its handling; on the other hand the presence of coal improves the surface quality of the castings, increasing its refractoriness decreasing pores and releasing volatile reducing agents

Packaging Available

- Bulk, in tank truck
- 800/850 kg aprox. big-bags
- 25 kg paper bags