

CHAMOTTE N

Chemical Analysis (Standard)		
%	typical	guaranteed
Al ₂ O ₃	40.03	Min 38.0
SiO ₂	55.00	
Fe ₂ O ₃	1.20	Max 1.5
TiO ₂	3.00	—
CaO	0.20	—
MgO	0.09	—
Na ₂ O	0,10	Max 0.5
K ₂ O	0.10	

Physical Properties			
	typical	guaranteed	
Bulk Density	2,56	2,50	g/cm ³
Water absorption	1.36	—	%
Apparent Porosity	3	—	%