

CHAMOTTE N 38/40

Chemical Analysis (Standard)		
%	typical	guaranteed
Al ₂ O ₃	39.08	Min 38.0
SiO ₂	56.56	
Fe ₂ O ₃	1.12	Max 1.5
TiO ₂	2.81	—
CaO	0.22	—
MgO	< 0.1	—
Na ₂ O	0.07	Max 0.5
K ₂ O	< 0.1	

Physical Properties			
	typical	guaranteed	
Bulk Density	2,56	2,50	g/cm ³
Water absorption	1.36	—	%
Apparent Porosity	3	—	%