

# ELECTROFUSED MAGNESITE 97 %

<b>Chemical Analysis</b>		
%	Typical	Guaranteed
Al <sub>2</sub> O <sub>3</sub>	0.07	—
SiO <sub>2</sub>	0.52	—
Fe <sub>2</sub> O <sub>3</sub>	0.27	—
TiO <sub>2</sub>	—	—
CaO	1.38	—
MgO	97.75	Min 97.0
LOI	0.05	Max 0.20

<b>Physical Properties</b>			
	Typical	Guaranteed	
Bulk density	3.51-3.52	3.50	g/cm <sup>3</sup>

<b>Mineralogical Composition</b>	
Main phase	Magnesia
Secondary phase	

<b>Other information</b>
Magnesite calcined in electric arc furnaces.