

MULLCOR 60

Chemical Analysis (Standard)		
%	typical	guaranteed
Al ₂ O ₃	61,46	Min 59,00
SiO ₂	31,69	—
Fe ₂ O ₃	1,30	Max 1,70
TiO ₂	3,80	—
MgO	0,17	—
CaO	0,25	—
K ₂ O	0,06	—
Na ₂ O	0,28	—

Physical Properties			
	typical	guaranteed	standard
Bulk density	2,59		g/cm ³
Water absorption	2,75	—	%
Apparent Porosity	7	—	%

Mineralogic Composition	
Main Phase	Mullite ≈ 95 %
Secondary Phase	α - alumina ≈ 14 %