

T CLAY

Chemical Analysis	
%	Typical
Al ₂ O ₃	24,08
SiO ₂	67,18
Fe ₂ O ₃	0,25
TiO ₂	0,91
CaO	0,05
MgO	0,09
Na ₂ O	0,11
K ₂ O	2,90

Physical Properties			
	Typical	Guaranteed	

Mineralogical Composition	
Main Phase	Kaolinite
Secondary Phase	Montmorillinite

Other Information
Clay with low iron content.