

ACEGUNIT

Chemical Analysis	
%	
Al ₂ O ₃	3,0
CaO	34,0
Na ₂ O	19,0

Physical Properties	
Appearance	White powder
Bulk density	0,90 g/cm ³

Other information
<p>Setting time (VICAT), with a 5% of acegunit over the cement weight.</p> <p>Initial setting: 2 minutes Final setting: 4 minutes</p>