

CEMENT A-725

Chemical Analysis		
%	Typical	Guaranteed
Al ₂ O ₃	51.8	Min 50 %
SiO ₂	7.3	Max 8.0 %
Fe ₂ O ₃	1.8	Max 2.5,0 %
CaO	33.2	Min 32 %

Physical Properties			
Guaranteed			
	1 day	3 days	
Compressive Strength	55	65	Mpa
Flexural Strength	6	7	Mpa
Setting time	Initial	60	Minutes
	Final	360	Minutes