

CHAMOTTE 42/44

Chemical Analysis (Standard)		
%	typical	guaranteed
Al ₂ O ₃	43.02	Min 42.0
SiO ₂	52.13	
Fe ₂ O ₃	1.46	Max 1.8
TiO ₂	2.90	—
CaO	0.15	—
MgO	0.12	—
Na ₂ O	0.05	Max 0.35
K ₂ O	0.16	

Physical Properties			
	typical	guaranteed	
Bulk Density	2,58	2,52	g/cm ³
Water absorption	1.27	—	%
Apparent Porosity	3	—	%