

CHAMOTTE N 44/46

Chemical Analysis (Standard)		
%	typical	guaranteed
Al ₂ O ₃	44.76	Min 44.0
SiO ₂	49.89	
Fe ₂ O ₃	1.25	Max 1.5
TiO ₂	3.01	—
CaO	0.22	—
MgO	0.21	—
Na ₂ O	0.10	Max 0.35
K ₂ O	0.09	

Physical Properties			
	typical	guaranteed	
Bulk Density	2,62	2,55	g/cm ³
Water absorption	1.53	—	%
Apparent Porosity	4	—	%